



Polyester, C033

Polyester, Foam (PU)

Last Changed

22-12-2009

Properties	Standard (Test method)	Unit	Value
Cellular structure			Open Celled
Colour			Antracit Gray - Black
Density	ISO 845	kg/m ³	26-28
Hardness (CDH 40%)	ISO 3386	kPa	3,2 - 4,8
Elongation	ISO 1798	%	180
Tensile strength	ISO 1798	kPa	150
Burning rate	FMVSS 302	(mm/min)	<100
UV Resistant			YES

Miscellaneous:

Product:

Polyurethan foam, Polyester base.

Regilen 28 x FR / 60 PPI, Black

Porosity:

REGI RPA-1007 z/cm 60/70

Storage:

It is recommended by app. 20 °C (long-term storage)

Mounting:

By about 20 °C - and on VERY clean surfaces (Be absolutely sure to remove all grease and oil on the surface). When the material is mounted upside down, it is recommendable to secure the application with bands or screws.

The information provided in this data sheet is in good faith. No liability is, however, accepted for errors and omission and in no circumstances shall B6 Akustik be liable in damages for any loss or injury arising directly or as a consequence of the publication of this data sheet.