



PVC Foil

Foils, Surfaces

Last Changed

01-01-2008

Properties	Standard (Test method)	Unit	Value
Colour			Black, Gray etc.
Density	ISO 1183	g/m ³	1,27 (+/- 0,02 g)
Hardness	ISO 868	SHORE ° B	31
Hardness	ISO 868	SHORE ° A	82
Thickness	ISO 4591	mm	0,30
Temperature - short time		°C	-40 to + 115
Fire resistance	FMVSS 302	mm/min	<100

Miscellaneous:

Product specification:

PVC foil 30 My.

Black (8011) - Light Gray (7202) - Gray (7173) - Yellow (6659)

Storage:

It is recommended by app. 20 °C (long-term storage)

The information provided in this data sheet is in good faith. No liability is, however, accepted for errors and omission and in no circumstances shall B6 Akustik be liable in damages for any loss or injury arising directly or as a consequence of the publication of this data sheet.