



Measurement of Sound Absorption (coefficient α)

The sound absorption coefficient is the percentage of incident sound energy that, rather than being reflected, is converted to other forms of energy such as heat.

Material:	Spec-isolering
Applicant:	PU-20-B6A3

Date:	11-10-2007
Measured by:	PAN

Measure condition:	
Measurements require careful control of temperature and humidity in an impedance tube in accordance with ISO 10534-2.	
Distance mic. 1:	450 mm
Distance mic. 2:	375 mm

Hz / α	PU-20-B6A3				
125	0,043	-	-	-	-
160	0,075	-	-	-	-
200	0,142	-	-	-	-
250	0,190	-	-	-	-
315	0,295	-	-	-	-
400	0,389	-	-	-	-
500	0,503	-	-	-	-
630	0,537	-	-	-	-
800	0,468	-	-	-	-
1.000	0,460	-	-	-	-
1.250	0,566	-	-	-	-
1.600	0,754	-	-	-	-
1.715	0,766	-	-	-	-

(This item is a combination material, with havey layer Bitumen and PU foam)
(Reduce noise and vibration)

